

Technical datasheet No.: **1307.16**

Product: VALMEX® FR 700 MEHATOP F1 - type I

Article No.: 7205 5246

Type of coating and finish			
Type of coating	PVC		
Finish	Multi-composed PVDF-lacquer system on both sides, Titaniumdioxide (TiO₂) front side primer, low-wick, protected against microbial and fungal attack, UV-protected		
Burning behaviour	BS 7837, California T 19, D.M. 26.06.84 (UNI 9177): CL. 2, DIN 4102: B1, NFP 92507: M2, SIS 650082, EN 13501-1: B-s2-d0		
for Burning behaviour	always check the validity of fire certificate		
Total weight	700 g/m ²	EN ISO 2286-2	
Tensile strength warp/weft	3000 / 3000 N/50 mm	EN ISO 1421/V1	
Tear strength warp/weft	300 / 300 N	DIN 53363	
Adhesion	20 N/cm	PA 09.03 (intern)	
Cold resistance.	-40 °C	EN 1876-1	
High Temperature	+70 °C	PA 07.04 (intern)	
Light fastness	>6 Note, Value	EN ISO 105 B02	
Crack resistance	no cracks	100000 x	DIN 53359 A
Base fabric			
Material	PES low-wick		DIN EN ISO 2076
Yarn count	1100 dtex	DIN EN ISO 2060	
Weave	L 1/1		
Remarks	weldable without grinding and with common welding equipment, All values and Tio2 content related to standard white colour		

These indicated technical data are based on average results. Due to production procedures deviations up to -5% can occur. All technical data are in accordance with the present standard of knowledge and give product information without legal binding. All data apply to new products. Applications suggested do not release the customer to test material for its intended application.