



DIACIT

TECHNICAL INFORMATION

REFERENCE:

Available widths:

Composition

SPECIFICATIONS:

Weight (UNE-EN ISO 2286-2):

Water penetration resistance (UNE 20811):

Resistance to surface wetting -Spray Test (UNE 2492):

Oil repellency (AATCC 118):

Warp tensile strength (UNE-EN ISO 13934):

Weft tensile strength (UNE-EN ISO 13934):

Warp elongation at break (UNE-EN ISO 13934):

Weft elongation at break (UNE-EN ISO 13934):

Warp tearing resistance (UNE-EN ISO 4674-1):

Weft tearing resistance (UNE-EN ISO 4674-1):

Colour fastness to artificial weathering (UNE-EN ISO 105-B04)

Tolerance +/- 5%

Average Values. No contract information

ACRILLA - ACRILLA H

120 cm

SOLUTION DYED ACRYLIC

<u>ACRILLA</u>	<u>ACRILLA H</u>	
295	315	g/m ²
Min. 30	Min. 105	cm H ₂ O
Min. 90	Min. 90	
Min. 5	Min. 4	
130	147	daN/5 cm
75	74	daN/5 cm
30	35	%
20	30	%
5	5	daN
3	3	daN
7-8	7-8	

